



I. **AMENDMENTS TO THE CLAIMS:**

Claim 1. (Previously Presented) A method for removal of calcar deposits on a metal surface or its alloy, without abrasive or chemical systems, comprising:

pretreating a metal surface or its alloy to confer anti-calcar properties with a perfluoropolyether having a formula selected from:



wherein:

m' is an integer from 0 to 20;

L is an organic group selected from $-CH_2-(OCH_2CH_2)_n-$, $-CO-NR'-(CH_2)_q-$,
with R' = H or C₁ – C₄ alkyl;

n = 0 – 8, q = 1 – 8;

Z = H, alkaline metal or NR₄ group with R = H or C₁ – C₄ alkyl; Y = F, CF₃;

m = 1, 2, 3;

W is a group $-Si(R_1)_\alpha (OR_2)_{3-\alpha}$ with $\alpha = 0, 1, 2$, R₁ and R₂ equal to or different from each other are C₁ – C₆ alkyl groups optionally containing one or more ether O, C₆ – C₁₀ aryl groups, C₇ – C₁₂ alkyl – aryl or aryl – alkyl groups;

R_f has a number average molecular weight in the range 350 – 8,000 and comprises repeating units having at least one of the following structures, statistically placed along the chain:

(CFXO), (CF₂CF₂O), (CF₂CF₂CF₂O), (CF₂CF₂CF₂CF₂O),

(CR₄R₅CF₂CF₂O), (CF(CF₃)CF₂O), (CF₂CF(CF₃)O),

wherein

X = F, CF₃;

R₄ and R₅, equal to or different from each other, are selected from H, Cl, or perfluoroalkyl having from 1 to 4 carbon atoms;

placing the pretreated metal surface or its alloy in an environment wherein calcar deposits adhere to the pretreated metal surface or its alloy;

and washing the pretreated metal surface or its alloy having the calcar deposits with a running water flow at room temperature to remove the calcar deposits from the pretreated metal surface or its alloy.

Claim 2. (Previously Presented) The method of claim 1, wherein R_f is selected from the following structures:

1) - (CF₂O)_{a'} - (CF₂CF₂O)_{b'} -

with a'/b' in the range 0.5 - 2, extremes included, a' and b' being integers such as to give the above molecular weight;


2) - (C₃F₆O)_r - C₂F₄O)_b - (CFXO)_t -

with r/b = 0.5 - 2.0; (r+b)/t is comprised between 10 - 30, b, r and t being integers such as to give the above molecular weight, X has the above meaning;

3) - (C₃F₆O)_r - (CFXO)_{t'} -


t' can be 0;

when t' is different from 0 then $r'/t' = 10 - 30$, r' and t' being integers such as to give the above molecular weight; X has the above meaning;



wherein z is an integer such that the molecular weight is the above one;


y is an integer between 0 and 1 and $\text{R}'\text{f}$ is a fluoroalkylene group;



wherein:

q and s are integers such that the molecular weight is the above one;

R_4 , R_5 , $\text{R}'\text{f}$, y have the above meaning;



wherein $r'''/t''' = 10 - 30$,

r''' and t''' being integers such as to give the above molecular weight;

$\text{R}'\text{f}$ and y having the above meaning.

Claim 3. (Previously Presented) The method of claim 1, wherein in the compounds of structure (A) and (C) the end group of R_f is of the T-O- type, wherein T is a (per) fluoroalkyl group selected from: $-\text{CF}_3$, $-\text{C}_2\text{F}_5$, $-\text{C}_3\text{F}_7$, $-\text{CF}_2\text{Cl}$, $-\text{C}_2\text{F}_4\text{Cl}$, $-\text{C}_3\text{F}_6\text{Cl}$; optionally one or two F atoms can be substituted by H.

Claim 4. (Previously Presented) The method of claim 1, wherein a mixture of compounds (C) and (D) is used.

Claim 5. (Previously Presented) The method of claim 1, wherein the pretreatment is made by dipping, spin-coating, spraying, padding or brushing.

Claim 6. (Previously Presented) The method of claim 1, wherein the perfluoropolyether compounds of structure (C) and (D) are applied using formulations with solvent, solvent-water mixtures or prevailing aqueous formulations.

Claim 7. (Previously Presented) The method of claim 6, wherein the concentration of the perfluoropolyether compounds of structure (C) and (D) in the formulation is in the range 0.01 – 15% by weight.

Claim 8. (Previously Presented) The method of claim 1, wherein the perfluoropolyether compounds of structure (A) and (B) are applied using aqueous formulations or formulations having a polar solvent.

Claim 9. (Previously Presented) The method of claim 8, wherein the formulation contains an amount by weight of perfluoropolyether compound of structure (A) and (B) in the range 0.1 – 10% by weight

Claim 10. (Currently Amended) A method of conferring anti-corrosive properties to metal substrata and their alloys comprising:

(1) applying a (per)fluoropolyether having a formula selected from:





wherein:

L is an organic group selected from $-\text{CH}_2-(\text{OCH}_2\text{CH}_2)_n-$, $-\text{CO}-\text{NR}'-(\text{CH}_2)_q-$,
with $\text{R}' = \text{H}$ or $\text{C}_1 - \text{C}_4$ alkyl;

$n = 0 - 8$, $q = 1 - 8$;

$Y = \text{F}$, CF_3 ;

W is a group $-\text{Si}(\text{R}_1)_\alpha(\text{OR}_2)_{3-\alpha}$ with $\alpha = 0, 1, 2$, R_1 and R_2 equal to or different from each other are $\text{C}_1 - \text{C}_6$ alkyl groups optionally containing one or more ether O, $\text{C}_6 - \text{C}_{10}$ aryl groups, $\text{C}_7 - \text{C}_{12}$ alkyl-aryl or aryl-alkyl groups;

R_f has a number average molecular weight in the range 350 - 8,000 and comprises repeating units having at least one of the following structures, statistically placed along the chain:

(CFXO) , $(\text{CF}_2\text{CF}_2\text{O})$, $(\text{CF}_2\text{CF}_2\text{CF}_2\text{O})$, $(\text{CF}_2\text{CF}_2\text{CF}_2\text{CF}_2\text{O})$,
 $(\text{CR}_4\text{R}_5\text{CF}_2\text{CF}_2\text{O})$, $(\text{CF}(\text{CF}_3)\text{CF}_2\text{O})$, $(\text{CF}_2\text{CF}(\text{CF}_3)\text{O})$,

wherein

$\text{X} = \text{F}$, CF_3 ;

R_4 and R_5 , equal to or different from each other, are selected from H, Cl, or perfluoroalkyl having from 1 to 4 carbon atoms; and

(2) performing a thermal treatment of the metal substrates and their alloys at a temperature in the range of 60°C to 250°C.

Claim 11. (Canceled)

Claim 12. (Previously Presented) The method of claim 1 wherein m' is an integer from 0 to 4.

Claim 13. (Previously Presented) The method of claim 1 wherein $n = 1 - 3$.

Claim 14. (Previously Presented) The method of claim 1 wherein $q = 1 - 3$.

Claim 15. (Previously Presented) The method of claim 1 wherein $m = 1$ or 2.

Claim 16. (Previously Presented) The method of claim 1 wherein R_f has a number average molecular weight in the range 500 – 3,000.

Claim 17. (Previously Presented) The method of claim 2 wherein R'_f is a fluoroalkylene group having 1 – 4 carbon atoms.

Claim 18. (Previously Presented) The method of claim 3, wherein in T, one F atom is substituted by H.

Claim 19. (Previously Presented) The method of claim 7, wherein the concentration of the perfluoropoly ether compounds of structure (C) and (D) in the formulation is in the range 0.1 - 5% by weight.

Claim 20. (Previously Presented) The method of claim 9, wherein the amount by weight or weight of perfluoropolymer compound of structure (A) and (B) is in the range 0.5 – 5%.